

WHAT IS CLAIMED IS:

1. An aromatic dicarboxylic acid composition, essentially consisting of

(a) at least one aromatic dicarboxylic acid,

5 (b) 1-3000 ppm of at least one compound selected from the group consisting of 6-formyl-2-naphthoic acid, 6-methoxycarbonyl-2-naphthoic acid and trimellitic acid

(c) 1-1000 ppm of at least one alkali metal and

(d) 0-3000 ppm of at least one transition metal.

10 2. The composition of claim 1, which comprises 1-3000 ppm of at least one transition metal.

3. The composition of claim 1, wherein the alkali metal is selected from the group consisting of sodium and potassium.

15 4. The composition of claim 2, wherein the transition metal is selected from the group consisting of cobalt and manganese

5. The composition of claim 1, wherein the alkali metal is present in the form of an alkali metal salt selected from the group consisting of sulfate, carbonate, bicarbonate, nitrate, carboxylate and haloid.

20 6. The composition of claim 2, wherein the transition metal is present in the form of a transition metal salt selected from the group consisting of sulfate, carbonate, bicarbonate, nitrate, carboxylate and haloid.

0991209-073001  
FOOEEZD"6022T660

7. The composition of claim 5, wherein the mean volume particle size of the alkali metal salt is about 0.01-500 $\mu$ m.

8. The composition of claim 6, wherein the mean volume particle size of the transition metal salt is about 0.01-

5 500 $\mu$ m.

9. The composition of claim 1, wherein the aromatic dicarboxylic acid is 2,6-naphthalene dicarboxylic acid.

10. The composition of claim 1 which is used for preparation of a liquid crystalline polyester resin.

10 11. A liquid crystalline polyester resin comprising

(a) at least one repeat unit derived from an aromatic dicarboxylic acid;


(b) at least one monomer unit derived from a compound selected from the group consisting of 6-formyl-2-naphthoic acid, 6-methoxycarbonyl-2-naphthoic acid and trimellitic acid in an amount of 0.1-100 mmol % based on the total monomer units constituting the polyester;

(c) 1-100 ppm of at least one alkali metal.

15 12. The liquid crystalline polyester resin, further comprising 1-300 ppm of at least one transition metal.

20 13. A liquid crystalline polyester resin of claim 11, comprising the repeat units of (I), (II) and at least one of (III) and (IV) as its principal repeat units.

09917209.073001  
FOUWZ06027660




(I)




(II)

5

wherein Ar<sub>1</sub> represents ring moiety selected from the group consisting of benzene, naphthalene, biphenyl, biphenyl ether and biphenyl alkane wherein the alkane moiety has 1-4 carbon atoms and said ring moiety may be substituted by alkyl, alkoxy, or halogen atom



(III)



(IV)

10

100529-6027550